

Test Result SVR 10

Type : Natural rubber SVR 10

Date tested : May 25, 2012

Property	Samples No.			SVR 10 Limit
	1/209	2/209	3/209	
DIRT %	0,20	0,19	0,20	0,08 max
ASH %	1,08	1,10	1,05	0,75 max
VOLATILE MATTER %	0,63	0,62	0,63	0,80 max
NIROGEN %	0,33	0,34	0,33	0,60 max
PO	33	34	33	30 min
PRI	76	78	78	50 min

All tests on the samples submitted are carried out according to Vietnamese Standard TCVN 3769:2004